



Classing Office	Week				Season			
	Gins	Tenderable (%)	Eligible (%)	Bales	Gins	Tenderable (%)	Eligible (%)	Bales
UPLAND								
Abilene	31	67.8	53.8	54,056	31	71.7	53.1	232,484
Corpus Christi	3	82.4	55.7	1,928	48	82.1	45.3	986,096
Dumas	26	60.5	39.3	52,608	37	59.2	33.4	899,759
Florence	48	69.6	50.4	163,497	48	70.8	50.6	770,283
Lamesa	26	74.8	52.2	42,264	27	77.9	54.2	134,105
Lubbock	54	70.0	47.6	209,815	55	70.8	46.1	810,379
Macon	75	90.9	76.9	305,842	76	90.6	76.4	1,366,984
Memphis	71	91.1	77.6	318,477	73	89.0	72.4	2,271,431
Rayville	8	35.0	12.4	3,755	20	62.9	37.1	242,985
Visalia	13	88.8	74.5	18,874	19	87.8	68.0	97,984
United States	355	81.0	64.2	1,171,116	434	79.8	58.3	7,812,490
AMERICAN PIMA								
Visalia	18			32,999	19			132,509
United States	18			32,999	19			132,509
United States all cotton	371			1,204,115	449			7,944,999

* Data withheld to avoid disclosure of individual gin or less than 500 bales classed.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 11 & 21	1-2	Pct. 21.5	Pct. 30.0	Pct. 5.5	Pct. 28.3	Pct. 5.9	Pct. 4.2	Pct. 6.0	Pct. 4.5	Pct. 42.8	Pct. 55.2
	3	5.3	9.6	12.7	18.8	2.7	3.6	4.2	3.2	5.5	8.4
	4	0.2	1.4	0.2	1.7	0.2	0.1	0.1	0.1	0.1	0.4
	5	*	0.1	-	*	*	*	*	*	*	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	27.1	41.2	18.4	48.8	8.9	8.0	10.4	7.8	48.5
31	1-2	10.4	6.4	3.7	2.6	8.3	8.1	13.3	11.3	9.9	5.8
	3	19.2	13.3	31.0	5.9	34.0	36.0	42.1	44.5	19.3	10.7
	4	5.0	5.3	8.3	1.8	12.7	12.7	13.3	14.5	5.5	3.6
	5	0.9	1.5	0.7	0.1	0.7	0.8	1.1	1.0	0.5	0.6
	6	0.1	0.2	-	*	*	*	*	*	*	0.1
	7	*	*	-	*	-	-	*	*	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	35.6	26.7	43.7	10.5	55.7	57.7	69.8	71.3	35.2
41	1-2	0.7	0.4	0.3	0.4	0.3	0.3	0.3	0.3	0.1	*
	3	5.8	3.1	5.0	1.9	8.9	9.3	6.5	6.4	1.3	0.5
	4	6.0	3.0	9.8	1.0	18.5	16.9	9.6	10.2	2.5	1.3
	5	2.9	1.9	2.4	0.2	6.5	5.7	2.7	3.1	2.1	1.1
	6	0.9	0.8	-	*	0.5	0.6	0.2	0.3	1.2	0.5
	7	0.2	0.2	-	*	*	*	*	*	0.4	0.2
	8	*	*	-	*	-	*	-	-	-	-
	Total	----	16.6	9.3	17.5	3.5	34.6	32.8	19.3	20.1	7.6
51	1-2	-	*	0.3	*	-	*	*	*	-	-
	3	*	*	1.4	0.3	*	*	*	*	-	-
	4	0.1	*	1.2	0.2	0.1	0.1	*	*	-	-
	5	0.1	*	0.1	0.1	*	*	*	*	*	*
	6	0.1	*	-	*	*	*	*	*	*	*
	7	0.1	*	-	*	-	*	-	*	0.1	*
	8	*	0.1	-	-	-	*	-	-	-	-
	Total	----	0.4	0.2	3.0	0.6	0.1	0.2	*	*	0.1
61	1-2	-	-	-	*	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	*	-	-	*	*	-	-
	5	-	-	-	*	-	*	-	-	-	-
	6	-	-	-	-	-	*	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	*	-	-	-	-	-	-	-	-
	Total	----	-	*	-	*	-	*	*	*	-
71	1-2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	*	-	-	-	-	-	-
	4	-	-	-	-	-	-	-	-	-	-
	5	-	-	-	-	-	-	-	-	-	-
	6	-	-	-	-	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	-	*	-	-	-	-	-
12 & 22	1-2	2.6	4.9	5.9	18.0	*	*	*	*	3.1	5.8
	3	1.5	4.6	0.1	8.8	*	*	*	*	0.7	1.8
	4	0.3	1.2	-	1.0	-	*	*	*	0.1	0.1
	5	*	0.1	-	0.1	*	*	*	*	-	*
	6	-	*	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	4.4	10.7	6.0	27.8	*	*	*	*	3.8
32	1-2	0.8	0.6	0.1	0.8	*	*	*	*	1.1	0.7
	3	2.8	2.1	0.2	2.0	0.1	0.4	0.1	0.2	2.1	1.5
	4	2.2	2.1	1.0	0.9	0.1	0.2	*	0.1	0.7	0.6
	5	0.6	0.8	0.2	0.2	0.1	*	*	*	*	0.1
	6	*	0.1	-	*	*	*	*	*	*	*
	7	-	*	-	*	-	*	-	-	-	-
	8	-	*	-	*	-	-	-	-	-	-
	Total	----	6.4	5.7	1.6	3.8	0.3	0.6	0.1	0.4	3.9
42	1-2	*	*	0.1	0.2	*	*	*	*	*	*
	3	0.6	0.3	0.7	0.8	0.1	0.2	*	0.1	0.1	*
	4	1.9	0.7	0.9	0.4	0.1	0.3	*	0.1	0.1	0.1
	5	2.7	1.2	0.2	0.1	0.1	0.1	*	*	0.1	0.1
	6	1.6	0.9	-	*	*	*	*	*	*	*
	7	0.5	0.4	-	*	-	*	*	*	*	*
	8	0.1	*	-	*	-	*	-	-	-	-
	Total	----	7.4	3.7	1.9	1.6	0.3	0.6	0.1	0.3	0.3

* Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality Designation	Leaf	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Color 52	1-2	-	*	0.8	*	-	-	-	-	-	-
	3	*	*	2.2	0.2	-	*	*	*	-	-
	4	*	*	0.7	0.1	*	*	-	*	*	*
	5	*	*	0.2	*	*	*	-	*	*	*
	6	0.1	0.1	-	*	-	*	-	*	*	*
	7	0.2	0.1	-	*	-	*	-	*	-	-
	8	0.1	0.1	-	-	-	*	-	-	-	-
	Total	----	0.5	0.3	3.8	0.4	*	*	*	*	*
62	1-2	-	-	0.1	*	-	-	-	-	-	-
	3	-	-	0.4	*	-	-	-	-	-	-
	4	-	-	0.3	*	-	-	-	*	-	-
	5	-	-	-	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	0.7	*	-	-	-	*	-
13 & 23	1-2	*	0.4	0.6	1.1	-	-	-	*	0.2	0.2
	3	0.2	0.5	0.2	0.8	-	-	-	*	*	0.1
	4	*	0.1	-	0.2	-	*	-	*	*	*
	5	*	*	-	*	-	*	-	-	-	*
	6	-	-	-	*	-	*	-	-	-	-
	7	-	-	-	*	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.3	1.0	0.8	2.1	-	*	-	*	0.2
33	1-2	*	*	-	0.1	-	*	-	*	0.2	0.1
	3	0.3	0.2	0.3	0.2	*	*	*	*	0.2	0.1
	4	0.3	0.3	0.1	0.2	*	*	*	*	0.1	0.1
	5	0.1	0.1	-	0.1	*	*	*	*	*	*
	6	*	*	-	*	*	*	-	-	-	*
	7	-	*	-	*	-	-	-	-	-	*
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	0.7	0.7	0.4	0.6	*	*	0.1	*	0.4
43	1-2	-	*	-	*	-	*	-	*	-	-
	3	*	*	0.1	*	-	*	*	*	*	*
	4	0.2	0.1	0.2	*	-	*	-	*	-	*
	5	0.3	0.2	-	*	*	*	*	*	-	*
	6	0.1	0.1	-	*	*	*	*	*	-	*
	7	*	*	-	*	-	-	-	*	-	-
	8	*	*	-	*	-	*	-	-	-	-
	Total	----	0.5	0.3	0.3	0.2	*	*	*	*	*
53	1-2	-	-	-	*	-	-	-	-	-	-
	3	-	-	0.2	*	-	-	-	-	-	-
	4	-	*	0.5	*	-	-	-	*	-	-
	5	*	*	-	*	-	-	*	*	-	-
	6	*	*	-	*	-	-	-	*	-	-
	7	-	*	-	*	-	-	*	*	-	-
	8	*	*	-	*	-	-	-	-	-	-
	Total	----	*	*	0.6	*	-	-	*	*	-
63	1-2	-	-	-	*	-	-	-	-	-	*
	3	-	-	0.3	*	-	-	-	-	-	-
	4	-	-	0.9	*	-	-	-	-	-	-
	5	-	-	0.4	*	-	-	-	-	-	-
	6	-	-	-	*	-	-	-	-	-	-
	7	-	-	-	-	-	-	-	-	-	-
	8	-	-	-	-	-	-	-	-	-	-
	Total	----	-	-	1.6	*	-	-	-	-	-
24 - 54	1-8	0.2	0.1	-	*	-	*	*	*	-	0.1
25 - 35	1-8	-	-	-	-	-	-	-	-	-	-
81 - 85	1-8	*	*	-	*	-	-	-	-	-	-
STAPLE											
28 & Shorter		-	-	-	-	-	-	-	-	-	-
29		-	-	0.1	*	-	-	-	-	-	-
30		*	*	0.6	*	-	-	-	*	*	*
31		0.2	0.3	1.7	0.3	-	-	*	*	0.3	0.3
32		1.6	1.7	2.0	1.7	*	*	0.1	0.1	1.8	1.6
33		3.9	3.7	5.5	6.6	0.1	0.4	1.9	1.9	5.3	5.8
34		10.4	8.5	6.2	19.1	1.3	3.2	8.7	8.6	13.6	14.0
35		15.0	14.3	3.2	27.7	5.0	9.8	20.9	21.3	20.8	23.1
36		20.3	20.9	8.8	22.3	15.3	22.3	31.9	32.2	25.3	24.9
37		24.0	28.8	19.4	14.6	46.6	44.1	28.2	28.5	24.7	22.5
38		13.7	14.2	32.5	5.2	24.0	15.8	6.7	6.0	6.5	6.0
39		8.6	6.1	19.0	2.2	6.9	3.8	1.3	1.3	1.4	1.4
40 & Longer		2.1	1.5	1.1	0.3	0.8	0.5	0.1	0.1	0.2	0.3
Average Staple		36.31	36.31	36.93	35.39	37.10	36.72	36.01	36.00	35.70	35.63
Average Length		1.13	1.13	1.15	1.10	1.16	1.15	1.12	1.12	1.11	1.11

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 11 & 21	1-2	Pct. 31.8	Pct. 40.1	Pct. 2.6	Pct. 2.7	Pct. 11.0	Pct. 11.2	Pct. 1.1	Pct. 3.2	Pct. 83.0	Pct. 67.2	
	3	9.5	11.4	2.9	2.4	5.3	4.7	1.4	2.2	4.4	7.7	
	4	0.3	0.5	0.2	0.2	0.2	0.2	-	*	0.1	0.5	
	5	*	*	*	*	*	*	-	*	-	*	
	6	-	*	-	*	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	41.7	52.0	5.8	5.2	16.5	16.1	2.5	5.5	87.4	75.5
	31	1-2	13.2	8.7	9.0	10.2	19.6	19.1	3.8	7.0	6.9	6.2
3		25.4	17.5	34.2	36.8	37.6	39.9	15.6	22.5	3.7	6.1	
4		6.0	5.1	12.5	12.7	9.3	9.9	4.8	6.2	0.8	4.0	
5		0.3	0.5	1.3	1.2	0.7	0.7	0.1	0.3	*	0.8	
6		*	*	0.1	0.1	*	*	-	*	-	*	
7		-	*	*	*	*	*	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
Total		----	45.0	31.7	57.2	61.0	67.4	69.7	24.3	36.1	11.5	17.0
41		1-2	0.1	0.1	1.2	1.1	0.8	0.5	1.7	1.2	*	*
	3	1.2	0.6	14.7	13.1	6.8	5.6	26.0	15.4	0.1	0.1	
	4	2.2	1.2	14.3	12.5	6.2	5.8	27.6	16.0	*	0.3	
	5	1.1	0.7	3.9	3.3	1.8	1.7	3.4	3.9	*	0.2	
	6	0.3	0.3	0.5	0.4	0.2	0.2	0.2	0.3	*	*	
	7	0.1	0.1	0.1	*	*	*	-	*	-	-	
	8	*	*	-	*	-	-	-	*	-	-	
	Total	----	4.9	2.8	34.8	30.5	15.8	14.0	58.9	36.9	0.2	0.6
	51	1-2	*	*	*	*	*	*	-	*	-	-
3		*	*	0.2	0.1	*	*	0.3	0.2	-	-	
4		*	*	0.2	0.1	*	*	0.7	0.5	-	-	
5		*	*	0.1	*	*	*	0.9	0.6	-	-	
6		*	*	*	*	*	*	1.0	0.1	-	-	
7		*	*	*	*	*	*	-	*	-	-	
8		*	*	-	-	-	-	-	-	-	-	
Total		----	0.1	*	0.5	0.2	0.1	0.1	2.9	1.4	-	-
61		1-2	*	*	-	*	-	*	-	-	-	-
	3	-	-	-	*	-	*	-	-	-	-	
	4	-	-	*	*	-	*	-	-	-	-	
	5	-	-	-	*	*	*	-	-	-	-	
	6	-	-	-	*	-	*	-	*	-	-	
	7	-	-	-	*	-	*	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	*	*	*	*	*	*	-	*	-	-
	71	1-2	-	-	-	-	-	-	-	-	-	-
3		-	-	-	-	-	-	-	-	-	-	
4		-	-	-	-	-	-	-	-	-	-	
5		-	-	-	-	-	-	-	-	-	-	
6		-	-	-	-	-	-	-	-	-	-	
7		-	-	-	-	-	-	-	-	-	-	
8		-	-	-	-	-	-	-	-	-	-	
Total		----	-	-	-	-	-	-	-	-	-	-
12 & 22		1-2	1.2	3.8	*	*	*	*	-	1.7	0.2	3.7
	3	1.0	2.9	*	*	*	*	0.2	1.2	0.2	1.3	
	4	0.1	0.5	*	*	*	*	*	0.1	-	0.1	
	5	*	*	-	-	-	-	-	*	-	-	
	6	-	*	-	-	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	2.3	7.2	*	*	*	*	0.2	3.1	0.4	5.1
	32	1-2	0.7	0.6	*	0.1	*	*	0.1	1.0	*	0.2
3		1.9	2.1	0.4	0.6	*	*	0.8	3.7	0.1	0.6	
4		0.9	1.2	0.2	0.3	*	*	0.4	1.4	0.1	0.4	
5		0.2	0.3	*	*	*	*	0.1	0.2	*	0.2	
6		*	*	*	*	-	*	-	*	-	*	
7		*	*	*	*	-	-	-	*	-	-	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	3.7	4.2	0.6	1.0	0.1	0.1	1.4	6.4	0.3	1.4
42		1-2	*	*	*	*	*	*	1.0	0.4	-	*
	3	0.1	0.1	0.4	0.7	*	*	4.5	3.9	-	*	
	4	0.4	0.2	0.5	0.8	*	*	1.2	3.8	-	*	
	5	0.5	0.3	0.1	0.3	*	*	0.4	1.2	*	*	
	6	0.3	0.2	*	*	*	*	0.3	0.2	-	*	
	7	0.1	0.1	*	*	-	*	*	*	-	-	
	8	*	*	-	*	-	-	-	-	-	-	
	Total	----	1.4	0.9	1.0	1.9	0.1	0.1	7.4	9.5	*	0.1

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality Designation	Leaf	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA		
		Week	Season	Week	Season	Week	Season	Week	Season	Week	Season	
Color 52	1 - 2	-	-	*	*	-	*	-	*	-	-	
	3	*	*	*	*	*	*	0.2	0.1	-	-	
	4	*	*	0.1	*	*	*	0.2	0.2	-	-	
	5	*	*	*	*	*	*	0.7	0.2	-	-	
	6	*	*	*	*	-	*	0.7	0.1	-	-	
	7	*	*	*	*	-	*	-	*	-	-	
	8	*	*	-	-	-	-	-	-	-	-	
	Total	----	*	*	0.1	0.1	*	*	1.7	0.7	-	-
	62	1 - 2	-	-	-	-	-	-	-	-	-	-
3		-	-	-	*	-	-	-	*	-	-	
4		-	-	-	*	-	-	-	*	-	-	
5		-	-	-	*	-	-	-	-	-	-	
6		-	-	-	*	-	-	-	-	-	-	
7		*	*	-	-	-	-	-	-	-	-	
8		*	*	-	-	-	-	-	-	-	-	
Total		----	*	*	-	*	-	-	-	*	-	-
13 & 23		1 - 2	0.1	0.1	*	*	-	-	-	*	0.1	0.1
	3	0.1	0.2	*	*	-	-	-	0.1	*	*	
	4	*	0.1	-	-	-	-	-	*	-	-	
	5	-	*	-	-	-	-	-	*	-	-	
	6	-	*	-	-	-	-	-	*	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	-	-	-	-	-	-	-	-	-	
	Total	----	0.2	0.4	*	*	-	-	-	0.2	0.1	0.1
	33	1 - 2	*	*	*	*	*	*	-	*	-	*
3		0.2	0.2	*	*	*	*	-	*	*	*	
4		0.1	0.2	*	*	*	*	-	*	*	*	
5		*	0.1	*	*	*	*	-	*	-	-	
6		*	*	-	-	-	-	-	*	-	-	
7		-	*	-	-	-	-	-	-	-	-	
8		-	*	-	-	-	-	-	-	-	-	
Total		----	0.3	0.4	*	*	*	*	-	0.1	0.1	0.1
43		1 - 2	-	*	*	*	*	*	-	*	-	-
	3	*	*	*	*	*	*	0.2	*	*	*	
	4	0.1	*	*	*	*	*	0.2	0.1	*	*	
	5	0.2	0.1	*	*	*	*	0.2	0.1	0.1	*	
	6	0.1	0.1	*	*	*	*	0.1	0.1	-	-	
	7	*	*	*	*	-	-	-	*	-	-	
	8	*	*	-	-	-	-	-	-	-	-	
	Total	----	0.4	0.3	*	*	*	*	0.6	0.2	0.1	*
	53	1 - 2	-	-	-	-	-	*	-	-	-	-
3		-	*	-	*	-	*	-	*	-	-	
4		-	-	-	*	-	-	-	*	-	-	
5		*	*	-	*	-	*	-	*	-	-	
6		*	*	*	*	-	-	-	*	-	-	
7		*	*	-	-	-	-	-	*	-	-	
8		*	*	-	-	-	-	-	-	-	-	
Total		----	*	*	*	*	-	*	-	*	-	-
63		1 - 2	-	-	-	-	-	-	-	-	-	-
	3	-	-	-	-	-	-	-	-	-	-	
	4	-	-	-	*	-	-	-	*	-	-	
	5	-	*	-	-	-	-	-	-	-	-	
	6	-	-	-	*	-	-	-	-	-	-	
	7	-	-	-	-	-	-	-	-	-	-	
	8	-	*	-	-	-	-	-	-	-	-	
	Total	----	-	*	-	*	-	-	-	*	-	-
	24 - 54	1 - 8	*	0.1	*	*	-	-	0.1	*	-	-
25 - 35	1 - 8	-	-	-	-	-	-	-	-	-	-	
81 - 85	1 - 8	*	*	*	*	-	-	-	-	-	-	
STAPLE												
28 & Shorter		-	-	-	-	-	-	-	-	-	-	
29		*	*	-	-	-	-	-	-	-	-	
30		0.1	0.1	*	*	*	*	-	-	-	-	
31		0.5	0.5	*	*	-	*	-	*	-	-	
32		1.9	1.8	0.2	0.3	*	*	*	0.4	-	-	
33		5.6	5.0	1.4	1.8	*	0.1	0.8	2.5	0.2	0.1	
34		11.7	11.1	5.1	7.6	0.2	0.4	2.8	7.4	0.5	1.1	
35		19.8	18.6	15.2	18.6	4.0	5.1	5.0	16.6	2.4	9.2	
36		23.4	23.2	27.4	28.8	18.5	20.2	8.2	26.9	11.3	20.5	
37		22.5	24.3	36.1	31.9	45.1	48.5	60.3	29.4	36.3	34.0	
38		9.1	9.6	11.4	8.8	24.8	20.5	22.1	11.5	30.7	18.1	
39		3.7	4.2	2.9	2.0	6.5	4.6	0.7	4.6	14.4	11.6	
40 & Longer		1.6	1.6	0.4	0.3	0.8	0.7	-	0.7	4.2	5.4	
Average Staple		35.88	35.96	36.39	36.16	37.13	37.00	36.94	36.29	37.54	37.15	
Average Length		1.12	1.12	1.13	1.13	1.16	1.16	1.16	1.13	1.17	1.16	

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	10.6	7.9	0.7	0.1	*	*	1.7	1.2	3.2	2.1
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.3	0.9	3.0	0.4	*	*	0.3	0.3	0.1	0.2
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	-	*	-	-	*	*	-	-
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	0.2	0.6	-	*	*	*	*	0.2
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	-	*	-	*	-	*	-	-
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	-	*	-	*	-	*	-	*	-	-
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	0.1	0.1	*	*	*	*	*	*
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/22 & Below	0.1	0.1	2.9	0.5	-	-	-	-	*	*
23	0.1	0.2	0.4	0.6	-	-	-	-	*	*
24	0.2	0.4	0.6	1.4	*	*	*	*	0.2	0.2
25	1.0	0.9	0.8	2.7	*	*	*	*	0.6	0.6
26	2.4	1.7	2.3	5.1	0.2	0.1	0.2	0.1	1.9	2.3
27	4.6	3.4	3.2	8.2	1.0	0.9	0.9	0.7	4.0	4.9
28	7.7	6.3	4.8	11.3	3.9	3.6	5.5	4.5	9.3	9.8
29	11.6	9.6	7.5	14.2	10.8	11.7	18.3	15.7	14.8	14.4
30	16.0	13.5	19.2	14.7	20.8	24.1	30.6	28.0	20.7	19.2
31	16.8	15.2	28.3	12.5	27.8	30.1	24.6	27.0	20.2	19.2
32	13.0	15.0	19.7	10.5	21.7	18.8	12.7	14.9	13.5	13.1
33	11.0	14.5	8.1	8.7	8.6	7.3	5.3	6.5	8.4	8.7
34	8.9	12.4	1.8	5.4	3.3	2.5	1.6	1.9	4.1	4.9
35	4.7	5.4	0.3	2.8	1.4	0.7	0.4	0.5	1.7	1.9
36	1.6	1.2	0.1	1.1	0.4	0.2	*	0.1	0.6	0.7
37	0.4	0.3	-	0.2	0.1	*	*	*	0.2	0.1
38	*	*	-	*	-	-	-	-	*	*
39	*	*	-	*	-	-	-	-	-	*
40 & Above	-	-	-	-	-	-	-	-	*	*
Average	31.34	31.72	30.73	30.36	31.43	31.27	30.86	31.04	30.89	30.89
Mike										
2.4 & Below	*	*	-	*	-	-	-	-	-	*
2.5	0.3	0.1	-	*	-	*	-	*	-	*
2.6	0.2	0.1	-	0.1	-	*	-	*	*	*
2.7	0.3	0.2	-	0.1	-	*	-	*	*	*
2.8	0.3	0.4	-	0.1	-	*	*	*	*	*
2.9	0.7	0.7	-	0.2	*	*	*	*	*	*
3.0	1.2	1.1	-	0.2	*	*	*	*	*	0.1
3.1	0.8	1.4	-	0.4	*	*	*	*	0.1	0.1
3.2	0.9	1.8	0.2	0.6	*	*	*	*	0.1	0.2
3.3	1.7	1.9	0.7	0.8	*	*	0.1	*	0.2	0.4
3.4	1.4	2.5	0.8	1.1	0.1	*	0.1	0.1	0.5	0.5
3.5	1.9	3.0	0.7	1.3	0.2	*	0.2	0.1	0.6	0.5
3.6	2.8	3.1	0.5	1.7	0.3	0.1	0.3	0.2	1.1	0.8
3.7	3.3	3.8	0.1	2.2	0.4	0.1	0.5	0.4	1.7	1.2
3.8	4.7	4.5	0.2	3.1	0.4	0.1	0.9	0.7	2.0	2.2
3.9	5.5	5.3	0.8	4.0	0.4	0.2	1.1	1.1	3.5	3.1
4.0	6.0	6.2	2.9	5.3	0.8	0.4	1.5	1.9	3.7	3.3
4.1	7.4	6.9	3.9	6.8	1.6	0.9	3.0	3.0	3.7	3.8
4.2	7.2	7.3	1.8	8.7	2.6	1.6	4.3	4.2	5.5	6.0
4.3	8.1	8.2	3.5	10.2	3.9	2.6	5.7	5.5	7.8	7.2
4.4	9.1	8.1	6.3	10.8	5.9	4.0	7.6	6.8	8.1	7.7
4.5	9.4	8.4	9.9	10.7	6.8	5.9	8.1	8.2	8.8	8.9
4.6	7.8	7.4	20.4	9.5	7.7	8.0	9.4	9.6	8.7	10.3
4.7	5.2	5.8	24.6	7.6	9.3	10.2	9.9	10.5	9.2	11.1
4.8	4.1	4.3	16.2	5.6	9.7	12.4	9.7	10.5	9.6	10.2
4.9	3.3	3.1	5.8	3.8	11.2	13.8	9.4	9.9	8.0	7.2
5.0	2.8	2.1	0.8	2.4	12.0	12.9	8.9	9.2	6.4	5.4
5.1	2.0	1.3	-	1.6	11.0	10.5	7.2	7.1	3.8	3.9
5.2	0.8	0.7	-	0.8	6.4	7.9	5.4	5.2	2.0	2.4
5.3	0.7	0.3	-	0.4	5.0	4.6	3.6	3.2	2.2	2.0
5.4	0.1	0.1	-	0.1	2.4	2.4	1.8	1.5	1.4	1.1
5.5 & Above	*	*	-	0.1	1.7	1.5	1.3	1.1	1.4	0.6
Average	4.23	4.18	4.56	4.34	4.80	4.85	4.70	4.71	4.55	4.55

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality Designation	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
Extraneous Matter	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
Bark - Level 1	11.0	9.2	0.5	0.4	*	*	0.1	0.6	0.2	0.1
Bark - Level 2	-	-	-	-	-	-	-	-	-	-
Grass - Level 1	0.1	0.1	0.1	0.1	0.1	*	-	*	*	0.1
Grass - Level 2	-	-	-	-	-	-	-	-	-	-
Prep - Level 1	-	*	*	*	-	*	-	*	-	*
Prep - Level 2	-	-	-	-	-	-	-	-	-	-
Seed Coat - Level 1	*	*	0.1	0.1	*	*	-	*	3.2	0.7
Seed Coat - Level 2	-	-	-	-	-	-	-	-	-	-
Oil - Level 1	-	*	*	*	*	*	-	*	*	*
Oil - Level 2	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 1	-	-	-	-	-	-	-	-	-	-
Spindle Twist - Level 2	-	-	-	-	-	-	-	-	-	-
Other - Level 1	*	*	*	*	-	-	-	*	0.1	*
Other - Level 2	-	-	-	-	-	-	-	-	-	-
Plastic - Level 1	*	*	*	*	*	*	-	*	0.1	0.1
Plastic - Level 2	-	-	-	-	-	-	-	-	-	-
STRENGTH 1/										
22 & Below	*	*	-	*	-	*	-	-	-	-
23	*	*	*	*	*	*	-	-	-	*
24	0.1	0.1	*	*	*	*	0.1	0.1	-	0.1
25	0.4	0.5	*	0.1	*	*	3.5	0.4	*	0.4
26	1.3	1.5	0.2	0.3	*	0.1	0.9	1.2	0.2	1.9
27	3.7	4.0	1.4	1.7	0.4	0.7	1.6	3.2	0.3	3.5
28	7.8	8.4	5.2	6.4	3.1	5.8	1.9	6.4	1.4	7.2
29	13.0	13.4	14.9	15.9	18.8	23.7	4.3	11.9	7.0	12.1
30	15.9	16.8	26.1	25.8	41.6	38.3	6.0	22.3	14.9	13.1
31	16.8	17.9	24.8	24.5	27.0	22.5	27.2	27.0	19.5	12.9
32	16.2	16.0	15.2	14.8	7.4	6.9	33.5	17.5	18.8	12.7
33	11.7	11.0	7.5	6.6	1.2	1.5	18.2	7.1	11.0	9.9
34	7.2	6.1	3.1	2.6	0.3	0.3	2.6	1.8	10.2	8.5
35	4.0	3.0	1.1	0.9	*	0.1	0.2	0.7	6.6	6.3
36	1.4	1.0	0.3	0.4	*	*	0.1	0.3	4.5	4.0
37	0.5	0.3	0.1	0.1	*	*	*	*	3.4	3.9
38	*	*	*	*	-	-	-	*	1.6	2.7
39	-	-	-	*	-	-	-	-	0.3	0.6
40 & Above	-	-	-	-	-	-	-	-	0.1	0.2
Average	31.43	31.23	31.12	31.01	30.65	30.50	31.71	30.99	32.65	32.11
Mike										
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-
2.5	0.1	*	-	*	-	-	-	-	-	-
2.6	0.1	0.1	*	*	-	-	-	-	*	*
2.7	0.1	0.1	*	*	-	-	-	*	*	*
2.8	0.1	0.2	*	*	-	-	-	*	*	*
2.9	0.2	0.2	*	*	-	-	-	*	-	*
3.0	0.3	0.3	*	*	*	*	-	*	-	0.1
3.1	0.4	0.4	*	*	0.1	*	0.1	0.1	0.1	0.1
3.2	0.5	0.5	0.1	*	0.1	*	0.1	0.1	0.1	0.2
3.3	0.8	0.7	0.1	*	0.1	*	0.1	0.1	0.1	0.2
3.4	1.1	0.9	0.1	0.1	0.3	0.1	-	0.3	0.4	0.4
3.5	1.4	1.2	0.2	0.2	0.4	0.2	0.3	0.5	0.7	0.6
3.6	1.8	1.6	0.3	0.3	0.8	0.3	0.2	0.5	1.0	0.9
3.7	2.1	1.9	0.7	0.6	1.3	0.6	0.7	0.6	1.2	1.5
3.8	2.4	2.3	1.1	1.2	1.9	1.0	0.3	0.9	2.5	2.7
3.9	2.7	2.7	2.3	2.3	2.8	1.6	0.1	1.2	4.3	3.4
4.0	3.4	3.3	4.2	4.0	4.1	2.6	0.6	1.6	7.0	5.2
4.1	4.0	4.1	6.0	6.0	5.0	4.0	0.1	2.7	9.2	6.2
4.2	5.0	5.0	8.4	8.4	6.7	5.9	0.2	4.0	9.1	8.1
4.3	5.8	6.0	10.0	10.5	8.9	8.5	4.2	5.5	6.1	9.2
4.4	6.9	7.3	11.8	12.1	11.0	11.2	3.2	6.8	7.7	10.2
4.5	8.4	8.6	12.7	12.5	11.7	12.4	2.3	8.2	9.6	10.8
4.6	9.7	9.7	11.7	11.8	13.2	13.0	4.7	10.4	10.9	10.4
4.7	10.7	10.4	10.1	10.3	11.2	11.7	7.4	11.1	10.2	8.8
4.8	10.4	10.0	8.2	8.2	7.4	9.5	12.5	11.4	7.9	6.4
4.9	8.1	8.1	5.6	5.7	5.1	6.7	9.6	9.1	4.9	5.4
5.0	5.0	5.5	3.3	3.2	3.6	4.6	18.3	8.1	2.8	4.0
5.1	3.3	3.4	1.6	1.6	2.4	2.8	15.8	5.7	1.1	1.7
5.2	2.1	2.2	0.8	0.7	1.2	1.4	8.3	4.2	1.4	1.5
5.3	1.4	1.4	0.4	0.3	0.5	0.7	5.8	2.8	0.9	1.2
5.4	1.0	1.0	0.2	0.2	0.1	0.4	3.8	2.1	0.8	0.4
5.5 & Above	0.7	1.0	0.2	0.1	*	0.4	1.5	1.7	0.1	0.1
Average	4.49	4.50	4.48	4.48	4.48	4.55	4.90	4.68	4.42	4.44

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).
 * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality Designation	ABILENE		CORPUS CHRISTI		DUMAS		FLORENCE		LAMESA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
MIKE	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.	Pct.
2.4 & Below	*	*	-	*	-	-	-	-	-	*
2.5 - 2.6	0.5	0.1	-	0.1	-	*	-	*	*	*
2.7 - 2.9	1.3	1.2	-	0.4	*	*	*	*	0.1	0.1
3.0 - 3.2	2.9	4.3	0.2	1.2	*	*	*	*	0.2	0.4
3.3 - 3.4	3.1	4.4	1.5	1.9	0.1	*	0.2	0.1	0.7	0.8
3.5 - 3.6	4.7	6.1	1.1	3.0	0.5	0.1	0.5	0.3	1.6	1.2
3.7 - 4.2	34.1	34.0	9.6	30.0	6.2	3.3	11.4	11.3	20.0	19.4
4.3 - 4.9	47.1	45.2	86.7	58.1	54.6	56.9	59.7	60.9	60.2	62.6
5.0 - 5.2	5.6	4.1	0.8	4.7	29.4	31.3	21.4	21.5	12.2	11.7
5.3 & Above	0.8	0.4	-	0.6	9.2	8.5	6.8	5.8	5.0	3.7
Average	4.23	4.18	4.56	4.34	4.80	4.85	4.70	4.71	4.55	4.55
Leaf										
1 - 2	36.1	42.8	17.3	51.4	14.5	12.7	19.7	16.0	57.3	67.7
3	35.8	33.9	54.6	39.7	45.9	49.6	53.0	54.4	29.1	23.2
4	16.4	14.2	24.0	7.7	31.7	30.3	23.1	25.0	9.1	6.3
5	7.6	5.9	4.1	0.9	7.5	6.8	3.8	4.1	2.7	1.9
6	2.9	2.3	-	0.2	0.5	0.6	0.3	0.3	1.3	0.7
7	0.9	0.7	-	*	*	*	*	*	0.5	0.2
8	0.3	0.2	-	*	-	*	-	-	-	-
Average	3.02	2.84	3.13	2.50	3.33	3.33	3.11	3.18	2.43	2.17
HVI Trash 1/										
00	*	*	-	*	-	*	-	*	0.1	0.6
01	14.1	17.3	4.1	15.5	1.8	1.5	2.6	1.8	32.6	40.2
02	26.0	28.4	15.4	36.8	16.4	15.7	19.7	16.6	29.4	30.7
03	20.3	19.9	24.9	25.8	23.9	26.0	27.9	27.3	16.4	13.9
04	13.4	12.2	24.3	12.9	21.5	22.7	21.8	23.7	9.9	6.8
05	8.3	7.5	15.6	5.4	15.9	15.5	13.8	15.2	5.0	3.4
06	5.8	4.8	8.4	2.1	9.9	9.2	7.6	8.3	2.4	1.8
07	4.2	3.2	4.0	0.9	5.5	5.0	3.7	4.1	1.4	1.1
08	2.7	2.1	2.3	0.4	2.9	2.5	1.7	1.8	1.0	0.6
09	1.8	1.5	0.9	0.2	1.4	1.2	0.7	0.8	0.7	0.4
10	1.2	1.0	0.1	0.1	0.6	0.5	0.3	0.3	0.5	0.2
11	0.8	0.7	-	*	0.2	0.2	0.1	0.1	0.4	0.1
12	0.5	0.5	-	*	0.1	0.1	*	0.1	0.2	0.1
13	0.3	0.3	-	*	*	*	*	*	0.1	*
14	0.3	0.2	-	*	*	*	*	*	*	*
15	0.1	0.1	-	*	*	*	*	*	*	*
16	0.1	0.1	-	*	*	*	-	*	*	*
17	*	*	-	*	-	*	-	*	-	-
18 & Above	0.1	0.1	-	*	-	*	-	*	-	-
Average	0.36	0.34	0.39	0.27	0.41	0.41	0.38	0.39	0.26	0.22
UNIFORMITY 2/										
74 & Below	-	*	0.2	*	-	-	-	-	*	*
75	0.1	0.1	0.3	*	-	-	-	*	*	0.1
76	0.8	0.4	1.1	0.4	-	-	*	*	0.7	0.5
77	3.2	2.6	2.5	1.5	*	*	*	*	3.1	2.5
78	10.4	10.2	4.4	4.0	0.4	0.3	0.2	0.2	10.3	9.1
79	20.7	20.1	8.9	10.3	2.0	1.6	2.0	1.9	22.7	22.4
80	26.8	24.9	16.5	24.2	6.8	7.1	11.0	12.3	32.6	32.6
81	24.3	23.3	31.9	36.4	15.9	19.3	33.3	32.5	23.7	24.3
82	11.1	15.2	28.9	20.0	30.1	34.1	34.2	35.7	6.2	7.7
83	2.5	3.0	5.0	3.0	30.7	27.1	17.1	15.6	0.6	0.9
84	0.1	0.1	0.4	0.2	12.2	9.3	2.1	1.8	*	*
85 & Above	-	*	-	*	1.8	1.3	0.1	0.1	*	*
Average	80.45	80.58	81.19	81.06	82.68	82.55	82.04	82.01	80.28	80.37
Tenderable 3/	67.8	71.7	82.4	82.1	60.5	59.2	69.6	70.8	74.8	77.9
SAMPLES CLASSIFIED										
Week	54,056		1,928		52,608		163,497		42,264	
Season		232,484		986,096		899,759		770,283		134,105

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSIFIED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Quality MIKE	LUBBOCK		MACON		MEMPHIS		RAYVILLE		VISALIA	
	Week	Season	Week	Season	Week	Season	Week	Season	Week	Season
2.4 & Below	0.1	*	-	-	-	-	-	-	-	-
2.5 - 2.6	0.1	0.1	*	*	-	-	-	-	*	*
2.7 - 2.9	0.5	0.5	*	*	-	-	-	0.1	*	*
3.0 - 3.2	1.2	1.1	0.1	*	0.2	0.1	0.2	0.3	0.1	0.4
3.3 - 3.4	1.9	1.6	0.2	0.1	0.4	0.1	0.1	0.5	0.5	0.7
3.5 - 3.6	3.2	2.8	0.5	0.4	1.2	0.5	0.5	1.0	1.8	1.5
3.7 - 4.2	19.6	19.2	22.7	22.4	21.8	15.8	1.9	11.1	33.2	27.0
4.3 - 4.9	60.0	60.1	70.0	71.0	68.5	73.1	43.9	62.5	57.3	61.4
5.0 - 5.2	10.4	11.1	5.6	5.4	7.2	8.7	42.3	18.0	5.3	7.2
5.3 & Above	3.1	3.4	0.8	0.6	0.7	1.6	11.0	6.7	1.8	1.8
Average	4.49	4.50	4.48	4.48	4.48	4.55	4.90	4.68	4.42	4.44
Leaf										
1 - 2	47.2	53.3	13.0	14.0	31.4	30.9	7.7	14.6	90.2	77.4
3	39.4	34.9	52.7	53.7	49.8	50.3	49.1	49.4	8.6	15.9
4	10.1	9.0	28.1	26.7	15.9	16.0	35.2	28.4	1.0	5.3
5	2.2	1.9	5.5	4.9	2.6	2.5	5.8	6.6	0.1	1.2
6	0.7	0.6	0.6	0.5	0.2	0.3	2.2	0.9	*	0.1
7	0.2	0.2	0.1	0.1	*	*	*	0.1	-	-
8	0.1	0.1	-	*	-	-	-	*	-	-
Average	2.63	2.52	3.28	3.24	2.88	2.89	3.46	3.29	1.61	1.98
HVI Trash 1/										
00	*	*	*	*	*	*	-	-	*	0.1
01	17.4	21.2	1.6	1.8	6.2	6.7	0.2	2.3	63.4	48.2
02	36.1	36.4	16.4	17.4	29.2	27.9	8.7	16.2	27.4	31.9
03	23.5	21.0	28.1	29.0	28.8	28.3	20.4	26.1	6.4	9.7
04	11.7	10.5	24.0	23.9	17.8	18.4	24.8	22.7	1.8	4.4
05	5.5	5.2	15.2	14.4	9.5	9.9	20.2	15.1	0.6	2.6
06	2.6	2.5	7.9	7.3	4.6	4.8	12.3	8.7	0.3	1.5
07	1.3	1.3	3.8	3.4	2.1	2.2	6.1	4.5	0.1	0.8
08	0.7	0.7	1.7	1.5	1.0	1.0	2.5	2.2	*	0.3
09	0.4	0.4	0.7	0.7	0.4	0.4	1.7	1.1	*	0.2
10	0.3	0.3	0.3	0.3	0.2	0.2	1.0	0.6	*	0.1
11	0.2	0.2	0.1	0.1	0.1	0.1	1.1	0.3	-	*
12	0.1	0.1	0.1	*	*	*	0.4	0.1	-	*
13	0.1	0.1	*	*	*	*	0.5	0.1	-	*
14	*	*	*	*	*	*	0.2	*	-	*
15	*	*	*	*	*	*	-	-	-	-
16	*	*	*	*	-	-	-	-	-	-
17	*	*	*	*	-	-	-	-	-	-
18 & Above	*	*	*	*	-	-	-	-	-	-
Average	0.28	0.27	0.39	0.38	0.33	0.33	0.47	0.40	0.15	0.19
UNIFORMITY 2/										
74 & Below	*	*	-	*	-	-	-	-	-	-
75	0.3	0.2	-	*	*	*	-	-	-	*
76	1.0	0.9	*	*	*	*	-	-	-	*
77	3.2	3.0	0.1	0.2	*	*	0.1	0.1	*	0.3
78	9.3	8.8	1.0	1.5	0.1	0.1	0.5	1.3	0.4	2.5
79	20.6	19.6	5.3	8.5	0.7	1.1	2.1	5.5	3.5	10.1
80	29.6	27.9	20.1	26.3	7.6	8.6	4.5	15.2	20.3	23.5
81	23.3	23.8	35.2	35.5	25.3	24.0	7.8	29.9	38.4	29.0
82	10.0	11.8	27.0	21.6	37.4	37.5	26.5	31.5	23.1	19.3
83	2.3	3.3	9.6	5.7	25.8	25.3	49.8	15.0	9.7	9.8
84	0.4	0.6	1.6	0.7	2.7	3.3	7.9	1.5	4.5	5.0
85 & Above	*	0.1	0.1	*	0.2	0.2	0.8	0.1	0.3	0.6
Average	80.43	80.54	81.62	81.32	82.34	82.32	82.85	81.80	81.72	81.49
Tenderable 3/	70.0	70.8	90.9	90.6	91.1	89.0	35.0	62.9	88.8	87.8
SAMPLES CLASSIFIED										
Week	209,815		305,842		318,477		3,755		18,874	
Season		810,379		1,366,984		2,271,431		242,985		97,984

1/ Measure of the percent of the sample surface covered by the trash particles as determined by a video scanner; 12 indicates that trash particles cover 1.2 percent of the sample surface. Trash particles include extraneous matter such as grass, bark, etc. 2/ Measure of the relative uniformity of the length of fibers; if all fibers were the same length, uniformity index would equal 100. 3/ Tenderable for delivery on ICE No. 2 futures contracts. * Less than 0.05 percent.

QUALITY OF COTTON CLASSED FOR PRODUCERS BY CLASSING OFFICE
For The Week Ending Nov 30, 2023

Color Grade	Leaf	VISALIA		Quality Designation	VISALIA	
		Week	Season		Week	Season
01	1	12.1	11.3	MIKE		
	2	16.9	14.9	2.4 & Below	-	-
	3	0.7	0.5	2.5 - 2.6	*	*
	4	*	*	2.7 - 2.9	0.3	0.1
	5	-	-	3.0 - 3.2	1.8	1.2
	6	-	-	3.3 - 3.4	4.0	3.2
	7	-	-	3.5 - 3.6	12.0	11.0
Total -----		29.8	26.7	3.7 - 4.2	73.9	78.9
02	1	6.1	8.7	4.3 - 4.9	7.9	5.6
	2	38.0	45.3	5.0 - 5.2	-	*
	3	12.7	9.9	5.3 & Above	-	*
	4	0.7	0.5	Average	3.90	3.89
	5	*	*	ALL RANGE MIKE		
	6	-	-	2.4 & Below	-	-
	7	*	*	2.5	-	*
Total -----		57.5	64.4	2.6	*	*
03	1	*	0.1	2.7	*	*
	2	3.8	3.0	2.8	0.1	*
	3	6.1	4.0	2.9	0.2	0.1
	4	1.1	0.9	3.0	0.2	0.1
	5	0.1	*	3.1	0.3	0.3
	6	*	*	3.2	1.3	0.7
	7	-	-	3.3	1.6	1.0
Total -----		11.2	8.1	3.4	2.3	2.2
04	1	-	-	3.5	4.8	4.2
	2	0.1	*	3.6	7.2	6.8
	3	0.6	0.3	3.7	7.8	9.7
	4	0.4	0.2	3.8	12.1	14.0
	5	0.1	*	3.9	16.5	17.3
	6	0.1	*	4.0	14.9	16.6
	7	-	-	4.1	12.9	13.4
Total -----		1.2	0.6	4.2	9.8	7.9
05	1	-	-	4.3	5.5	3.5
	2	-	*	4.4	2.1	1.5
	3	*	*	4.5	0.3	0.4
	4	*	*	4.6	*	0.1
	5	*	*	4.7	*	*
	6	0.1	*	4.8	-	*
	7	0.1	*	4.9	-	*
Total -----		0.2	0.1	5.0	-	*
06	1	-	-	5.1	-	*
	2	-	-	5.2	-	-
	3	-	-	5.3 & Above	-	*
	4	*	*	Average	3.90	3.89
	5	*	*	STRENGTH 1/		
	6	-	-	36 & Below	1.0	2.1
	7	*	*	37	2.8	4.0
Total -----		*	*	38	5.4	7.8
07	1	-	-	39	6.5	7.3
	2	-	-	40	6.4	5.5
	3	-	-	41	11.7	8.5
	4	-	-	42	18.7	14.8
	5	-	-	43	19.4	17.6
	6	-	-	44	14.7	14.9
	7	-	-	45	8.9	11.2
Total -----		-	-	46	3.6	4.8
STAPLE	44 & Shorter	0.7	1.0	47	0.6	1.2
	46	6.9	9.6	48 & Above	0.3	0.3
	48	30.1	36.5	Average	42.54	42.47
	50	51.0	45.2	UNIFORMITY		
	52 & Longer	11.3	7.7	83 & Below	0.1	0.1
Average Staple		49.31	48.98	84	2.1	3.7
Average Length		1.43	1.42	85	13.3	21.3
EXTRANEEOUS MATTER	Bark	*	*	86	47.8	48.1
	Grass	0.2	0.2	87	35.9	26.0
	Spindle Twist	0.3	0.2	88 & Above	0.8	0.7
	Preparation	*	*	Average	86.65	86.44
	All Other	*	*	Samples Classed		
				Week	32,999	
				Season		132,509

1/ Fiber strength expressed in terms of 1/8" gage (grams per tex).

* Less than 0.05 percent.